

Contact with unprotected steel supports

Introduction

Any supporting steel structure for roofing and walling made from ZINCALUME® aluminium/zinc/magnesium alloy-coated steel or COLORBOND® prepainted steel must be coated with an appropriate compatible material, preferably zinc or aluminium/zinc/magnesium alloy. The use of uncoated steel in either a hot rolled or cold rolled condition is discouraged as corrosion of the overlying roof sheeting is greatly enhanced. Where heavy steel sections such as hot rolled steel angles are necessary for structural requirements, the steel sections must be post painted with an appropriate high build industrial coating system or post galvanised.

In situations where there is a high condensation load (e.g. municipal water reservoirs), purlins may be subject to localised inundation of moisture, due to the profile of the roof sheeting made from ZINCALUME® steel or COLORBOND® steel. In such cases, BlueScope recommend that the purlins be post painted with an appropriate protective coating system.

In corrosive environments, where low coating mass zinc-coated steel purlins ($\leq 200\text{g/m}^2$ zinc coating) are used to support roof sheeting made from ZINCALUME® steel or COLORBOND® steel, the purlins may be subject to accelerated corrosion, such that the zinc coating is completely consumed. In such cases, the roof sheeting is then left in direct contact with the base steel of the purlins allowing sacrificial corrosion of the ZINCALUME® steel coating to occur. To avoid this situation, BlueScope recommend that heavy coating mass and/or post painted purlins be used.

In severe environments, where SUPERDURA® Stainless prepainted steel is specified for roof sheeting, BlueScope recommend that zinc-coated steel purlins be insulated from the roof sheeting, to avoid dissimilar metal corrosion (stainless steel/ zinc corrosion couple). This can be achieved by means of an inert polymer separation tape adhered to the top surface of the purlin.

Such procedures are regarded as imperative to prevent the deterioration of the steel member and consequently the rapid degradation of the roof sheeting.

Advice must be sought from reputable coating manufacturers and tape suppliers in regard to the specification of an appropriate protective system which will offer suitable corrosion resistance for the particular exposure environment.

steel.com.au

To ensure you have the
most current information

1800 800 789

steeldirect@bluescopesteel.com
For more information contact Steel Direct

