

TRU-SPEC®

coil plate steel

AS/NZS 1594 – HA3

General description

Hot rolled structural product with a minimum yield strength of 200 MPa, good ductility and excellent weldability. Stretch-levelled to remove internal stresses and for excellent flatness.

Normally supplied in the pickled and oiled condition.

Typical uses

- Structural members
- Roll forming applications
- Press brake forming applications
- General fabrications
- Galvanising applications

Features & benefits

- Guaranteed minimum strength levels
- Excellent weldability
- Very good formability

Warnings

This material should be used in conjunction with the appropriate design and welding standards.

An untrimmed edge (Mill Edge) may contain minor surface discontinuities as a result of the rolling process. It is recommended that customers satisfy themselves that the edge is suitable for the application.

Free from coil break for 3 months after production.

Material should be stored under cover to avoid issues with storage related corrosion.

Australian and International Standards

AS/NZS 1594:2002 (R2016)

AS/NZS 1365:1996 (R2016)

ISO 9001:2015 Quality System Certified



Supply conditions

	Normal	Optional
Thickness Range	3.0 – 6 mm *	-
Width Range	750 – 1550 mm *	-
Length Range	1200 – 12000 mm *	-
Surface Finish	Hot Rolled pickled and oiled	Black
Edge Condition	Untrimmed (Mill Edge)	Trimmed
Tolerance	AS/NZS 1365:1996 (R2016)	-
Flatness	Class A	-
Certification	BlueScope – Analysis and Mechanical tests	-

* Not all thickness, width & length combinations are available
Optional supply conditions are subject to dimensional restrictions

Chemical composition

Element	Guaranteed Maximum %
Carbon	0.08
Silicon	0.030
Manganese	0.40
Phosphorus	0.030
Sulfur	0.025
Aluminium	0.10
CEQ (IIW)	-

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

Mechanical properties

Tensile Properties (Longitudinal)		Guaranteed Value
Yield Strength (MPa)	Guaranteed Minimum	200
Tensile Strength (MPa)	Guaranteed Minimum	300
Elongation 80 mm (%)	Guaranteed Minimum	32% ($\leq 3\text{mm}$), 34% ($> 3\text{mm}$)
180° Bend (transverse)	Guaranteed Minimum	0t

t = thickness of test piece

Galvanised Coating Characteristics Related to Steel Composition

Category

A

Refer to Table 9.1 of AS/NZS 2312.2:2014

Where aesthetics are important or where particular coating thickness, surface smoothness or resistance to handling damage criteria exist, specialist advice on steel selection should be sought prior to fabrication of the article or hot dip galvanising.

Weldability Group

WTIA Group

1

Refer to WTIA Technical Note 1 or AS/NZS 1554.1:2014

Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994 (R2016))	Not deemed combustible (steel substrate) #

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

steel.com.au

To ensure you have the most current information

1800 024 402

steeldirect@bluescopesteel.com
For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. TRU-SPEC®, TRUSPEC®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2024 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved