

# **XLERPLATE<sup>®</sup> steel**

**SA/AS 1548 – PT460NRA (L0, L20)**

## **General description**

A fully killed, fine grained, carbon-manganese steel for boiler and pressure vessel applications, with a guaranteed minimum tensile strength of 460MPa. Produced by normalised rolling. Tested in the normalised and stress relieved condition.

## **Features & benefits**

- Guaranteed minimum strength levels
- Grades with elevated temperature properties available
- Grades available with guaranteed low temperature properties
- Excellent weldability
- Excellent formability
- This grade is recognised in the ASME material codes


## **Warnings**

This material should be used in conjunction with the appropriate pressure vessel design and welding standards.

Guidelines for cold bending, where fracture toughness is important are given in AS 4100:2020 and AS 1210:2010.

## **Australian and International Standards**

- AS 1548:2008 (R2018)
- AS/NZS 1365:1996 (R2016)
- ISO 9001:2015 Quality System Certified



## Normal / optional supply conditions

	Normal	Optional
<b>Thickness Range</b>	PT460NRA: 8mm - 100mm PT460NRAL20: 8mm – 40mm	-
<b>Availability</b>	Sizes outside standard plate offer – refer to XLERPLATE® size schedule 4	PT460NRAL0 is available by enquiry only
<b>Edge Condition</b>	Trimmed	-
<b>Tolerances</b>	Thickness: AS 1548:2008 (R2018) Others: AS/NZS 1365:1996 (R2016)	-
<b>Ultrasonic Inspection</b>	-	AS 1710:2007
<b>Surface Inspection</b>	BlueScope	Third party
<b>Certification</b>	BlueScope	Third party endorsed

Optional supply conditions may be subject to dimensional restrictions

## Chemical composition

Element	Guaranteed Maximum %
Carbon	0.20
Silicon	0.6
Manganese	1.70
Phosphorus	0.040
Sulfur	0.030
Chromium	0.25
Nickel	0.50
Copper	0.40
Molybdenum	0.10
Aluminium	0.10
Niobium**	0.010
Titanium	0.040
CEQ (IIW)	0.43

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

\*\* Niobium up to 0.030% may be added for L20, L40 and L50 designations

## Mechanical properties

Tensile Properties (Transverse)		Thickness (mm)			
		t ≤ 16	16 < t ≤ 40	40 < t ≤ 80	80 < t ≤ 100
<b>Yield Strength (MPa)</b>	Guaranteed Min	305	295	275	265
<b>Tensile Strength (MPa)</b>	Required	460 to 580	460 to 580	460 to 580	460 to 580
<b>Elongation 5.65√S<sub>0</sub> (%)</b>	Guaranteed Min	21	21	21	21

Charpy Impact Properties	Longitudinal on 10 x 10mm test piece	Test Temperature (°C)	Absorbed Energy (joules)	
			Avg. of 3	Individual
Guaranteed Min	460NR	0	31	23
Guaranteed Min	460NRL0	0	51	38
Guaranteed Min	460NRL20	-20	47	35

Formability	Thickness (mm)	Longitudinal	Transverse
Recommended min inside Radius	t ≤ 20	1.5t	1.0t
	20 < t ≤ 50	6.0t	4.0t
	t > 50	Hot Forming	

## Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994 (R2016))	Not deemed combustible (steel substrate) #

# These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

**[steel.com.au](http://steel.com.au)**

To ensure you have the most current information

**1800 024 402**

[steeldirect@bluescopesteel.com](mailto:steeldirect@bluescopesteel.com)  
For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. XLERPLATE®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.