

# TRU-SPEC<sup>®</sup>

## coil plate steel

### AS/NZS 1594 – HK1042

#### General description

---

Hot rolled carbon steel with a guaranteed chemical composition. Stretch-levelled to remove internal stresses and for excellent flatness.

#### Typical uses

---

Concrete mixer barrels

#### Features & benefits

---

Wear Resistance

#### Warnings

---

This material should be used in conjunction with the appropriate design and welding standards.

An untrimmed edge (Mill Edge) may contain minor surface discontinuities as a result of the rolling process. It is recommended that customers satisfy themselves that the edge is suitable for the application.

Free from coil break for 3 months after production.

Material should be stored under cover to avoid issues with storage related corrosion.

#### Australian and International Standards

---

AS/NZS 1594:2002 (R2016)

AS/NZS 1365:1996 (R2016)

ISO 9001:2015 Quality System Certified



## Supply conditions

	Normal	Optional
Thickness Range	3.8 – 8.0 mm *	-
Width Range	1351 – 1450 mm *	-
Surface Finish	Hot Rolled	-
Edge Condition	Untrimmed (Mill Edge)	-
Tolerance	AS/NZS 1365:1996 (R2016)	-
Flatness	Class A	-
Certification	BlueScope – Analysis only	-

\* Not all thickness & width combinations are available  
Optional supply conditions are subject to dimensional restrictions

## Chemical composition

Element	Guaranteed Range or Maximum %
Carbon	0.39 - 0.47
Silicon	0.50
Manganese	0.60 - 0.90
Phosphorus	0.040
Sulfur	0.030
Aluminium	0.10

## Mechanical properties

No guaranteed mechanical properties.

## Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994 (R2016))	Not deemed combustible (steel substrate) #

# These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

**[steel.com.au](http://steel.com.au)**

To ensure you have the most current information

**1800 024 402**

[steeldirect@bluescopesteel.com](mailto:steeldirect@bluescopesteel.com)  
For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited.  
© 2024 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.