

ZINCFORM® steel

G250 / G250S

General description

ZINCFORM® steel G250 is a hot-dipped zinc-coated structural steel with a spangled surface and guaranteed minimum yield strength of 250MPa, with good ductility. Suitable for severe rollforming.

ZINCFORM® steel G250S is skin passed to improve surface quality. This skin passed product is only available up to 2mm thick.

Typical uses

Rollformed structural sections, culverts¹.

Australian and International Standards

AS/NZS 1365:1996 (R2016)

AS 1397:2021

ISO 9001:2015 Quality System certified

Guaranteed properties of steel base

Mechanical properties	Guaranteed minimum
Yield Strength, MPa (longitudinal tensile)	250
Tensile Strength, MPa (longitudinal tensile)	320
Elongation on 80mm (≥ 0.60mm) %	22
180° Transverse Bend	0t

Chemical composition of steel base

Chemical properties	Guaranteed maximum %
Carbon – C	0.12
Manganese – Mn	0.50
Phosphorus – P	0.040
Sulphur – S	0.035

Metal coating adhesion – 180° bend test

Coating class	Result
Z100	0t
Z200	0t
Z275	0t
Z450	1t
Z600	2t

Where t = the diameter of mandrel in terms of thickness of product.

Dimensional capabilities

Thickness range (mm)	Max width (mm)
0.80 – 2.00	1530
2.01 – 3.50	1200 (G250 only)

Notes: Not every combination of thickness and width may be available. Supply conditions may be subject to dimensional restrictions and are subject to BlueScope Sales and Marketing confirmation. Slitting and shearing available on request from BlueScope Sales Offices. For requirements outside the standard product range please contact your local Sales Office.

Fire hazard properties

Test & Evaluation Methods	Range	Result
Simultaneous determination of ignitability, flame propagation, heat release and smoke release (AS/NZS 1530.3:1999 (R2016))	Ignitability Index (0 – 20)	0
	Spread of Flame Index (0 – 10)	0
	Heat Evolved Index (0 – 10)	0
	Smoke Developed Index (0 – 10)	1
NCC non-combustible material (NCC 2022)	National Construction Code, Building Code of Australia 2022; Volume 1 Part C1, C2D10, (5)	Non-combustible

Supply conditions

Attribute	Normal	Optional
Coating Class	Z275	Z200, Z450, Z600
Surface Condition	Spangled	Minimised Spangle
Surface Treatment	Passivated	-
Branding	Branded	-
Tolerance – Dimensions	Class A	Class B
Tolerance – Flatness	Class A	Class B

Important Notes: Optional supply conditions may be subject to dimensional restrictions.

Fabricating performance

Method	Rating
Bending	5
Drawing	3
Pressing	2
Rollforming	5
Lock Forming	-
Welding	5
Painting Pre-treatment	5

Where: 1 = Limited to 5 = Excellent or NR = Not Recommended

The ratings in this table are general indicators only, given as a guide to fabricating performance.

Important information

Skin-passing will generally give a marginally higher yield strength and marginally reduced % elongation.

Material should be used promptly (within six months) to avoid the possibility of a storage related corrosion. For selection of the most appropriate metallic coated steel, please refer to Technical Bulletins TB1a, TB1b, CTB21 and CTB22. For storage, rollforming lubricants and other information please refer to the Technical Bulletins.

1. Material used in buried corrugated metal structures (e.g. helically formed zinc-coated steel culverts) must be specified and installed in accordance with AS/NZS 2041.1 and AS/NZS 2041.4.

steel.com.au

To learn more about this product

1800 064 384

steeldirect@bluescopesteel.com

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope Steel Limited's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope Steel Limited for advice about your proposed use of this product, please contact Steel Direct. ZINCFORM®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2026 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.